


ANSI/NFSI B101.3-2012 Report

Material:
DAF - Speedy Vinyl
#7610 WET TESTING


Regan Scientific Instruments

05/24/2018, 8:45AM

Method: DCOF
Facility: 001
Location: 001
Result: 0.37
Distance: 04 in.
Temp/Hum: 72 F, 47%




1.




4.


1. Avg = 0.37, Min = 0.35, Max = 0.40




2. Avg = 0.35, Min = 0.34, Max = 0.36




3. Avg = 0.37, Min = 0.36, Max = 0.39




4. Avg = 0.37, Min = 0.35, Max = 0.39



5. Avg = 0.35, Min = 0.34, Max = 0.36



6. Avg = 0.38, Min = 0.37, Max = 0.40



Device: BOT-3000E (v2.02.03)
Serial No: 00329
Calibration: 08/11/2017
Verification: 05/02/2018, 3:28PM PASS
Meter: 40.3 hrs

Sensor: 00770
Type: Rubber
Manuf. date: 10/31/2013
Ref. offset: ----